

PP 350031 R

PP grey, reprocessed from industrial waste

Properties	Value	Unit	Test method
Melt flow	30-35	g/10 min	ISO1133
Tensile strenght modulus	1200	MPa	
Tensile strength	23,5	MPa	ISO 527-1
Charpy notched impact strength	4,3	kJ/m ²	ISO 179
Content of recycled base	>98%		
Color	Grey		

This composite is REACH compliant and can be used for injection molding.

Information relates to average values, which may vary.

It is the customer's responsibility to assure suitability by optimize conditions for use in their own products.

It is advised that the material is pre dried prior to use.

2020-04